

Water Reducible Primer

Technical Data Sheet (TDS)

Product Description

Crown Water Reducible Primer is one component water reducible general purpose fast dry primer.

Product features:

- Alkyd formula for interior/exterior use
- Easy application & Cleanup
- Excellent Flash Rust Resistance
- Available in various colors
- Lead, chromate, and heavy metal free
- VOC Compliant

Recommended Uses

Water Reducible Primer is intended for industrial applications either new build or maintenance.

Industries:

- Oilfield & Energy Service
- Industrial Equipment
- Construction Equipment
- Agricultural Equipment
- General Metal Applications

Mixing

Water Reducible Primer is a single component.

Stir each container thoroughly prior to use.

Product Characteristics

Typical Physical Properties	
Gloss:	Eggshell: <20 GU at 60°
Volume Solids: (Single Component Unreduced) P206 Red Oxide	32% ± 2%
Volume solids will vary by color	
VOC (Unreduced): EPA Method 24 P206 Red Oxide	143 g/l 1.194 lb /gal
VOC content will vary with each color	
Shelf Life:	
Water Reducible Primer	6 months
For unopened product (77°F (25°C))	
Weight Gallon: P206 Red Oxide	10.65 ± 0.2lb/gal

Surface Prep

Surfaces to be finished must be clean, dry and free of dirt, oil or any contamination that would adversely affect adhesion, protective properties or appearance of the coating.

Prepare metal surfaces to SSPC-SP2, SSPC-SP3 for normal requirements.

For questions regarding other substrates contact your Crown Representative.

Application Method

Water Reducible Primer can be applied by conventional air, air-assist airless, airless, or dip. May also be applied by brush or roller.

Water Reducible Primer

Technical Data Sheet (TDS)

Spray Gun Setup

Feed Type	Fluid Tip	Application Pressures (heel of gun)	Fluid Delivery
Siphon Feed	1.6-1.8 mm	40-50 psi	
Gravity Feed	1.6-1.8 mm	30-40 psi	
Pressure Feed	1.4-1.8 mm	50-60 psi	10-14 oz/min
Air Assist Airless	9 -17 Thou	1,000-1,800 psi	
Airless	11-15 Thou	1,700-3,000 psi	

Spray Viscosity

Supplied Viscosity - [77°F (25°C)]	
Stormer Viscometer	80 - 85 KU

Note: Material is packaged at a viscosity requiring little or no reduction for application by airless spray equipment.

Note: Spraying viscosity and thinning will depend on ambient conditions, spray equipment used, and the desired surface finish.

IF THINNING IS REQUIRED:

Use water to thin this product, or EB solvent may also be used in small amounts.

Film Build

Water Reducible Primer has a recommended film build thickness of:

Wet: WFT Unreduced	3.0 – 6.0 mils	75 – 150 microns
Dry: DFT	1.0 – 2.0 mils	25 – 50 microns

Theoretical coverage at 1.0 mil (25 microns)
 DFT: 513 ft² per gallon at 100% transfer efficiency.

Dry Times

	70°F (21°C)
To Touch	30 Minutes
To Handle	1 Hour
To Recoat	2 Hours
Through Dry	18 Hours

Optimum drying conditions are 60°F to 90°F (16°C to 32°C) at 50% R.H. Lower temperatures and high humidity will slow dry time. Surface must be dry and at least 5°F(3°C) above the dew point.

Note: Product may be force cured to enhance dry. Force cure temperatures in the range of 110-180°F may be utilized to accelerate water/solvent evaporation and speed oxidation.

Topcoating Information

Water Reducible Primer may be topcoated with most solventborne and waterborne Crown Topcoats.

Clean Up

Clean all equipment immediately after use with water. If equipment will not be utilized for an extended period, do a final flush with solvent such as EB or Acetone.

Ordering Information (sizing)

Package sizes available:
 Aerosol, 1 gallon, 5 gallons, 55 gallon drum, 300 gallon tote.
 Custom colors and sizes may be available.

Water Reducible Primer

Technical Data Sheet (TDS)

Environmental Conditions

For optimum coating performance product, substrate and ambient temperature should be above 50°F (10°C). To prevent condensation during application the surface temperature must always be 5°F (3°C) or more above the dew point.

Note: For use outside this range please contact your Crown Representative.

Safety Precautions

Please refer to all Safety Data Sheets (SDS) before using this product. SDS sheets can be obtained by contacting Crown Paint.

Specifications

Test	Test Method	Result
Salt Spray/Corrosion	ASTM B117	100 hours no field rusting, less than 1/8" creep from scribe 240 hours with topcoat
Adhesion:	ASTM D3359	5A; 100% B-1000 panel
Impact resistance	ASTM D2794	80 lbs direct 50 lbs reverse
Flexibility	ASTM D522	1/8 mandrel bend: Pass

Storage Conditions

Storing partially used container:

To store partially used container replace lid securely.

Mix thoroughly before reusing.

Keep from Freezing.

Store in Frost Free conditions.